

# TECHNICAL DATA SHEET

Issued: February 2018	<b>Product</b>	<b>RADIPOL® A40</b>
	<b>Product code</b>	P66F001
	<b>Colour</b>	NATURAL
	<b>References</b>	N° CAS. 32131-17-2

<b>Description</b>	Polyamide 6,6 Low viscosity
--------------------	-----------------------------

<b>Typical application</b>	Base polymer for compounding
----------------------------	------------------------------

<b>Material handling</b>	The material is supplied as granulate in bulk or packed in 500 or 1000 kg tight sealed containers. Store away from the direct rays of the sun in rooms provided with a proper ventilation. The packages must be kept closed until utilization. For the storing in silo use stainless steel or aluminum silos. Packaging materials: multilayer cardboard octabins with PE liner, polypropylene big bags with PE liner.
--------------------------	---

<b>Recycling</b>	The product can be reused after grinding and extrusion.
------------------	---

<b>Specification and regulation</b>	For safety instruction please refer to Material Safety Data Sheet.
-------------------------------------	--

<b>Adequacy declarations</b>	The product complies the Regulation: <ul style="list-style-type: none"> <li>- European Directive 2011/65/EC (and to successive updated and integrations)</li> <li>- Ministerial Decree 174/2004 (and to successive updated and integrations) relating to the use of materials that come into contact with drinking water.</li> </ul> Important: the above mentioned information relates only to the materials as delivered in their original packaging. It's not applicable to the product modified with or without addition of further additives.
------------------------------	--

	Properties	Method	Unit	Value	Test conditions
<b>Properties (1)</b> (Typical Values)	<b>Physical Properties</b>				
	<b>Density</b>	ISO1183	Kg/dm <sup>3</sup>	1,14	
	<b>Relative Viscosity</b>	Internal Method	-	2,45	Solvent: sulphuric acid 95.7% Polyamide concentration:0.01 g/ml
	<b>Chip Size</b>	-	mm	2,0x2,5x3,0	
	<b>Granulometry</b>	Internal Method	g/100 chips	1,9	
	<b>Yellow Index</b>	Internal Method	-	- 8 max	
	<b>Mechanical Properties</b>				
	<b>Tensile modulus</b>	ISO 527-2/1A	MPa	3000	DAM; vel. test 1mm/min
	<b>Yield stress</b>	ISO 527-2/1A	MPa	80	DAM; vel. test 5mm/min
	<b>Yield strain</b>	ISO 527-2/1A	%	5,1	DAM; vel. test 5mm/min
	<b>Nominal strain at break</b>	ISO 527-2/1A	%	25	DAM; vel. test 50mm/min
	<b>Flexural modulus</b>	ISO 178/1A	MPa	2800	DAM; vel. test 2mm/min
	<b>Flexural strength</b>	ISO 178/1A	MPa	121	DAM; vel. test 2mm/min
	<b>Charpy impact strength</b>	ISO 179 eU	KJ/m <sup>2</sup>	NB	DAM; T=23°C
	<b>Charpy notched impact strength</b>	ISO 179 eA	KJ/m <sup>2</sup>	4,8	DAM; T=23°C
<b>Thermal Properties</b>					
<b>Melting temperature</b>	ISO 11357-1-3	°C	260	Scanning rate 10°C/min	

Notes: (1) test specimens were obtained according ISO 1874-2.  
DAM = dry as moulded state