

Aeon
Accurate. Efficient. On time.

Aeon Laboratories, LLC
5835 N Genematas Dr
Tucson, AZ 85704 USA
520-690-0012
www.aeonlaboratories.com

Biobased Content Summary Report


2014-2-10

Prepared for: RADICI CHIMICA
Via Fauser 50 - 28100
Novara - Italy

Test method: ASTM D6866-12 (B)

Material	Sample ID	Analysis ID	Biobased Content
polymer	RADIPOL DC (PA6.10)	Aeon 001671	60%
polymer	RADIPOL DX (PA 10.10)	Aeon 001672	98%

Unless otherwise stated, the worst-case result uncertainty is less than 3%.



Aeon
Accurate. Efficient. On time.

Aeon Laboratories, LLC
5835 N Genematas Dr
Tucson, AZ 85704 USA
520-690-0012
www.aeonlaboratories.com

Biobased Content Analysis Report

2014-2-10

Prepared for: RADICI CHIMICA
Via Fauser 50 - 28100
Novara - Italy

Material Analyzed: polymer
Sample ID: RADIPOL DC (PA6.10)
Analysis ID: Aeon 001671
Test method: ASTM D6866-12 (B)


Biobased content: 60%

(carbon-neutral proportion)


(biobased carbon to total carbon)

Biobased vs Fossil Carbon Content

Determined by radiocarbon analysis



Unless otherwise stated, the worst-case result uncertainty is less than 3%.



Aeon
Accurate. Efficient. On time.

Aeon Laboratories, LLC
5835 N Genematas Dr
Tucson, AZ 85704 USA
520-690-0012
www.aeonlaboratories.com

Biobased Content Analysis Report

2014-2-10

Prepared for: RADICI CHIMICA
Via Fauser 50 - 28100
Novara - Italy

Material Analyzed: polymer
Sample ID: RADIPOL DX (PA 10.10)
Analysis ID: Aeon 001672
Test method: ASTM D6866-12 (B)


Biobased content: 98%

(carbon-neutral proportion)

(biobased carbon to total carbon)

Biobased vs Fossil Carbon Content

Determined by radiocarbon analysis



Unless otherwise stated, the worst-case result uncertainty is less than 3%.