

TECHNICAL DATA SHEET

Issued: February 2018	Product	RADIPOL® A40D
	Product code	P66F002
	Colour	NATURAL
	References	N° CAS. 32131-17-2

Description	Polyamide 6,6 Low viscosity, Dry
--------------------	----------------------------------

Typical application	Base polymer for dry blending, compounding, injection moulding
----------------------------	--

Material handling	The material is supplied as granulate, packed in 500 or 1000 kg tight sealed containers. Store away from the direct rays of the sun in rooms provided with a proper ventilation. The packages must be kept closed until utilization. For the storing in silo use stainless steel or aluminum silos. Packaging materials: multilayer cardboard octabins with PE liner or PE/Al/PET liner with barrier effect.
--------------------------	--

Recycling	The product can be reused after grinding and extrusion.
------------------	---

Specification and regulation	For safety instruction please refer to Material Safety Data Sheet.
-------------------------------------	--

Adequacy declarations	The product complies the Regulation: <ul style="list-style-type: none"> - European Directive 2011/65/EC (and to successive updated and integrations) - Ministerial Decree 174/2004 (and to successive updated and integrations) relating to the use of materials that come into contact with drinking water. Important: the above mentioned information relates only to the materials as delivered in their original packaging. It's not applicable to the product modified with or without addition of further additives.
------------------------------	--

	Properties	Method	Unit	Value	Test conditions
Properties (1) (Typical Values)	Physical Properties				
	Density	ISO1183	Kg/dm ³	1,14	
	Relative Viscosity	Internal Method	-	2,45	Solvent: sulphuric acid 95.7% Polyamide concentration:0.01 g/ml
	Chip Size	-	mm	2,0x2,5x3,0	
	Granulometry	Internal Method	g/100 chips	1,9	
	Yellow Index	Internal Method	-	- 6 max	
	Mechanical Properties				
	Tensile modulus	ISO 527-2/1A	MPa	3000	DAM; vel. test 1mm/min
	Yield stress	ISO 527-2/1A	MPa	80	DAM; vel. test 5mm/min
	Yield strain	ISO 527-2/1A	%	5,1	DAM; vel. test 5mm/min
	Nominal strain at break	ISO 527-2/1A	%	25	DAM; vel. test 50mm/min
	Flexural modulus	ISO 178/1A	MPa	2800	DAM; vel. test 2mm/min
	Flexural strength	ISO 178/1A	MPa	121	DAM; vel. test 2mm/min
	Charpy impact strength	ISO 179 eU	KJ/m ²	NB	DAM; T=23°C
	Charpy notched impact strength	ISO 179 eA	KJ/m ²	4,8	DAM; T=23°C
Thermal Properties					
Melting temperature	ISO 11357-1-3	°C	260	Scanning rate 10°C/min	

Notes: (1) test specimens were obtained according ISO 1874-2.
DAM = dry as moulded state